# KBS TERNISK BAPPORT

A short review of the formation, stability, and cementing properties of natural zeolites

**Arvid Jacobsson** 

Högskolan i Luleå 1977-10-03



A SHORT REVIEW OF THE FORMATION, STABILITY AND CEMENTING PROPERTIES OF NATURAL ZEOLITES

Arvid Jacobsson Högskolan i Luleå 1977-10-03

Denna rapport utgör redovisning av ett arbete som utförts på uppdrag av KBS. Slutsatser och värderingar i rapporten är författarens och behöver inte nödvändigtvis sammanfalla med uppdragsgivarens.

I slutet av rapporten har bifogats en förteckning över av KBS hittills publicerade tekniska rapporter i denna serie.

REPORT ON

A SHORT REVIEW OF THE FORMATION, STABILITY AND CEMENTING
PROPERTIES OF NATURAL
ZEOLITES
Lulea 1977-10-03

Lulea 1977 - 10 - 03
DIV. SOIL MECHANICS
A. JACOBSSON



A SHORT REVIEW OF THE FORMATION, STABILITY, AND CEMENTING PROPERTIES OF NATURAL ZEOLITES

### Introduction

The buffer mass for embedding nuclear waste canisters way down in tunnels or bore holes must fulfil a number of requirements. A 10-15% (by weight) sodium bentonite and 85-90% quartz mass has been suggested by Pusch & Jacobsson in a number of reports and this composition is at present the major alternative of the KBS commission. In most respects this buffer mass has excellent properties but its ion exchange capacity is moderate or low. For this reason zeolites have been suggested as an active component in the mass. The question has been, however, whether zeolites are chemically stable together with other minerals such as montmorillonite which still has to be used to give the buffer mass suitable plastic and permeable properties. It is the main object of this report to give an answer to this question and to illustrate any behaviour of zeolites relevant to the problem of finding a suitable buffer mass.

The author's intention has been to find out from geological formations containing zeolites, information concerning their genesis, environment at and after their formation, and their stability as single minerals or in a mixture with others.

Artificially zeolites will not be discussed as they will not give us the information we look for as regards to geological circumstances.

Table 1. Simple zeolite classification (Meier, 1968).

Species	Idealised unit cell Contents	Isostructural species
Analcime group Analcime	Na <sub>18</sub> [Al <sub>18</sub> Si <sub>32</sub> O <sub>98</sub> ],16H <sub>2</sub> O	Wairakite, leucite pollucite, viseite, kehoite
Natrolite group Natrolite Thomsonite Edingtonite	Na <sub>16</sub> [Al <sub>18</sub> Si <sub>24</sub> O <sub>80</sub> ],16H <sub>2</sub> O Na <sub>4</sub> Ca <sub>5</sub> [Al <sub>20</sub> Si <sub>20</sub> O <sub>80</sub> ],24H <sub>2</sub> O Ba <sub>2</sub> [Al <sub>4</sub> Si <sub>6</sub> O <sub>20</sub> ],8H <sub>2</sub> O	Mesolite, scolecite Gonnardite
Chabazite Group Gmelinite Chabazite	Nas[AlsSi <sub>16</sub> O <sub>48</sub> ],24H <sub>2</sub> O Ca <sub>2</sub> [Al <sub>4</sub> Si <sub>8</sub> O <sub>24</sub> ],13H <sub>2</sub> O	
Erionite Levynite	(Ca etc.)4.5[Al <sub>P</sub> Si <sub>27</sub> O <sub>72</sub> ],27H <sub>2</sub> O Ca <sub>3</sub> [Al <sub>2</sub> Si <sub>12</sub> O <sub>36</sub> ],18H <sub>2</sub> O	Linde T
Cancrinite hydrate Sodalite hydrate	Nan[AlaSinO24],5H2O Nan[AlaSinO24],4H2O	Nosean, Zhdanov's G, danalite, tugtupite, (synthetic Ca-alumino-sulphate)
Phillipsite group Phillipsite Gismondite	(K,Na) <sub>10</sub> [Al <sub>10</sub> Si <sub>22</sub> O <sub>84</sub> ],20H <sub>2</sub> O Ca <sub>4</sub> [Al <sub>8</sub> Si <sub>8</sub> O <sub>32</sub> ],16H <sub>2</sub> O	Harmotome
Barrer's Pl	Na <sub>6</sub> [Al <sub>6</sub> Si <sub>10</sub> O <sub>32</sub> ],15H <sub>2</sub> O	Linde B, garronite (?)
Heulandite group Brewsterite	(Sr,Ba,Ca) <sub>2</sub> [Al <sub>4</sub> Si <sub>12</sub> O <sub>32</sub> ],10H <sub>2</sub> O	
Heulandite	$Ca_4[\Lambda I_8Si_2*O_{72}],24H_2O$	Clinoptilolite
Stilbite	Na <sub>2</sub> Ca <sub>4</sub> [Al <sub>10</sub> Si <sub>26</sub> O <sub>72</sub> ].28H <sub>2</sub> O	
Mordenite group Mordenite Dachiardite	Nas[AlsSi40Os6],24H2O Nas[AlsSi40Os6],12H2O	
Epistilbite	Can[AlaSi18O48],16H2O	
Ferrierite Bikitaite	$\begin{array}{l} Na_{2}Mg_{2}[Al_{6}Si_{20}O_{72}],18H_{2}O\\ Li_{2}[Al_{2}Si_{4}O_{12}],2H_{2}O \end{array}$	
Faujasite group Faujasite Linde A	(Na <sub>2</sub> ,Ca) <sub>32</sub> [Al64Si <sub>128</sub> O <sub>384</sub> ],256H <sub>2</sub> O Na <sub>96</sub> [Al <sub>96</sub> Si <sub>96</sub> O <sub>384</sub> ],216H <sub>2</sub> O	Linde X, Linde Y ZK-4
ZK-5 Paulingite	Na <sub>24</sub> [Al <sub>24</sub> Si <sub>72</sub> O <sub>192</sub> ],90H <sub>2</sub> O (K <sub>2</sub> ,Ca,Na <sub>2</sub> ) <sub>152</sub> [Al <sub>152</sub> Si <sub>520</sub> O <sub>872</sub> ], ~ 700H <sub>2</sub> O	

Some of the more important zeolites we have to deal with and which are of special interest to us are classified in Table 1 according to Meier (1968).

Table 2 gives us a more practical classification.

Analcime or analcite, phillipsite, chabazite and clinoptilolite have been suggested as possible components in our buffer mass.

Since we will deal a little with geological periods of time in this report Table 3 is given here to show the terminology.

Table 2.

FORMULAE AND AVERAGE CHEMICAL COMPOSITIONS OF ZEOLITES MOST ABUNDANT IN SEDIMENTARY ROCKS (data from many sources). The compositions of all zeolites are extremely variable and, therefore, the percentages in the table can only be taken as approximations.

SiO <sub>2</sub>	$Al_2O_3$	CaO	Na <sub>2</sub> O	K <sub>2</sub> O	H <sub>2</sub> O	Others		
50.7	21.9	12.1	0.5	0.2	13.7	1.0		
55.9	23.0	11.7	1.1	0.2	8.5	0.1	Calcium-rich	
56.0	16.7	7.7	0.9	0.7	17.9	0.3		
60.3	12.7	3.2	2.9	0.9	18.1	0.9	Sodium and Calcium	
66.3	11.5	2.6	3.1	1.0	14.0	1.5	subequal	
47.2	27.1	0.2	15.4	0.3	9.6	0.4	Sodium-rich	
64.0	16.9	0.1	9.5	0.2	8.7	0.5		
64.7	12.4	1.5	3.8	3.1	13.2	1.4		
56.8	13.8	0.2	6.2	4.1	15.1	3.8	Potassium and sodium subequal	
54.1	17.7	1.3	3.8	6.8	15.6	0.2		
	50.7 55.9 56.0 60.3 66.3 47.2 64.0 64.7	50.7     21.9       55.9     23.0       56.0     16.7       60.3     12.7       66.3     11.5       47.2     27.1       64.0     16.9       64.7     12.4       56.8     13.8       54.1     17.7	50.7     21.9     12.1       55.9     23.0     11.7       56.0     16.7     7.7       60.3     12.7     3.2       66.3     11.5     2.6       47.2     27.1     0.2       64.0     16.9     0.1       64.7     12.4     1.5       56.8     13.8     0.2       54.1     17.7     1.3	50.7     21.9     12.1     0.5       55.9     23.0     11.7     1.1       56.0     16.7     7.7     0.9       60.3     12.7     3.2     2.9       66.3     11.5     2.6     3.1       47.2     27.1     0.2     15.4       64.0     16.9     0.1     9.5       64.7     12.4     1.5     3.8       56.8     13.8     0.2     6.2       54.1     17.7     1.3     3.8	50.7     21.9     12.1     0.5     0.2       55.9     23.0     11.7     1.1     0.2       56.0     16.7     7.7     0.9     0.7       60.3     12.7     3.2     2.9     0.9       66.3     11.5     2.6     3.1     1.0       47.2     27.1     0.2     15.4     0.3       64.0     16.9     0.1     9.5     0.2       64.7     12.4     1.5     3.8     3.1       56.8     13.8     0.2     6.2     4.1       54.1     17.7     1.3     3.8     6.8	50.7       21.9       12.1       0.5       0.2       13.7         55.9       23.0       11.7       1.1       0.2       8.5         56.0       16.7       7.7       0.9       0.7       17.9         60.3       12.7       3.2       2.9       0.9       18.1         66.3       11.5       2.6       3.1       1.0       14.0         47.2       27.1       0.2       15.4       0.3       9.6         64.0       16.9       0.1       9.5       0.2       8.7         64.7       12.4       1.5       3.8       3.1       13.2         56.8       13.8       0.2       6.2       4.1       15.1         54.1       17.7       1.3       3.8       6.8       15.6	50.7       21.9       12.1       0.5       0.2       13.7       1.0         55.9       23.0       11.7       1.1       0.2       8.5       0.1         56.0       16.7       7.7       0.9       0.7       17.9       0.3         60.3       12.7       3.2       2.9       0.9       18.1       0.9         66.3       11.5       2.6       3.1       1.0       14.0       1.5         47.2       27.1       0.2       15.4       0.3       9.6       0.4         64.0       16.9       0.1       9.5       0.2       8.7       0.5         64.7       12.4       1.5       3.8       3.1       13.2       1.4         56.8       13.8       0.2       6.2       4.1       15.1       3.8         54.1       17.7       1.3       3.8       6.8       15.6       0.2	

Table 3. Time concept of geological nature (Harbaugh, 1974).

Geologic time scale in general use. Names of epochs in Cenozoic Era are included; other epoch names are omitted. Estimates of time in millions of years are subject to change as age-dating techniques are improved and applied more widely.

Era	Perio	sd.	Epoch	Estimated Duration in Millions of Years	Estimated Millions of Years Ago	
Cenozoic	Neogen <b>e°</b>	Quaternary	(Recent)			
		Quaternary	Pleistocene	2.5	0 =	
			Pliocene	4.5	2.5 	
		Tertiary	Miocene	19	- 7 - 26	
	Paleogene*		Oligocene	12		
		! !	Eocene	16	<del></del> 38	
		!	Paleocene	11	<del></del> 54	
Mesozoic	Cretaceous			71	<b>-</b> 65	
	Jurassic			54	136	
	Triassic			35	190	
Paleozoic	Permian			55	-225	
	Carboniferoust	Pennsylvanian		30	-280	
		Mississippian		35	-310 -345	
	Devonian			50		
	Silurian			35	-39 <b>5</b>	
	Ordovician			70	- 430	
	Cambrian			70	- 500 - 570	

Precambrian

No worldwide divisions of the Precambrian have been devised, although various local classifications exist. By definition, the Precambrian embraces the time between the origin of the earth and the beginning of the Cambrian Period.

4000 + -

### Natural zeolites

Zeolites are formed in alcaline environment. Gases or solutions of volcanic origin, enriched saline solutions by evaporation are environments where zeolite formation takes place. In the case of saline or salinealcaline lakes with a high concentration of Na and in marine environments where the Na-content naturally is high, zeolitization occurs in soft sediments. In seawater pH is naturally about 8.0-8.4 but this situation is changed when the seawater penetrates the sediment. Atmospheric CO2 is removed and pH will then increase in the pore water to about 9 and this is favourable to the formation of a zeolite. Zeolitization in lakes and in the oceans can take place at low temperatures 2-3  $^{\circ}$ C according to Boles (1971). Ross (1941) noticed in his investigation of a transformed volcanic ash at Wikieup in Arizona that both analcite and bentonitic clays were formed from volcanic ash if the concentration of Mg and Ca is sufficiently high in the percolating solutions. If, on the other hand the concentration of Na-ions is high analcite will be formed. In Wikieup the mass ratio of analcite and bentonite was 4 to 1. This can, according to Ross, be taken as a proof of a coexistence between bentonite and analcite in solid rocks with the zeolites as cementing agent. Also Coombs (1965) noted that zeolite/montmorillonite can coexist but in the form of cemented solid rock (siltstone).

In deep drilling cores from the Pacific Ocean Couture (1977) found authigenic clinoptilolite in Cretaceous layers but montmorillonite and phillipsite in Tertiary layers. Biogene SiO<sub>2</sub> was said to contribute to the formation of clinoptilolite from the volcanic ash or glass while the phillipsite/montmorillonite is a direct product from the volcanic ash or glass. The origin of clinoptilolite can have been phillisite//montmorillonite.

According to many scientists an important factor for the formation of clinoptilolite may be that the Cretaceous sea was warmer than today. Couture (1977) believed that clinoptilolite must be either an authigenic formation or a redeposition of a material originating from the sea. No terrestrial sources are known to this author. Clinoptilolite occurs in abundance in Oligocenic and older sediments and rock-forming sediments. According to Sheppard (1973) clinoptilolites are mainly of Cenozoic age and their reaction is alcalic. The same author noticed that erionite and chabazite are not known from pre-Eocene formations.

Hay (1963) showed that zeolites occurring in Tanganyika are formed by Na-carbonate- and bicarbonate solutions which have affected volcanic glass and nepheline ash. The carbonate solutions are concentrated by evaporation in the soil and surface rock.

Combined hydratization and carbonization seem to be the reason for zeolitization.

$$3\text{H}_2\text{O} + \text{CO}_2^- + 3\text{NaAlSiO}_4 \rightarrow \text{NaAl(OH)}_2\text{CO}_3 + \text{Na}_2\text{Al}_2\text{Si}_3\text{O}_{10}^2\text{H}_2\text{O}$$
nepheline dawsonite natrolite

Further, Hay observed that phillipsite and calcite form the cement in recent and several thousand year old ash deposits.

In eolian tuffs which contain mineral grains, rock fragments and clay pellets of medium sand grain size the cementing mass consists of one or more zeolites. It can be added that cavities in all existing tuffs are often covered by phillipsite, sometimes also by chabazite, analcime and natrolite. Hayashi and Sudo (1957) described a rock-forming bentonite where the pore spaces among others contain zeolite (mordenite). The above mentioned (Hay, 1963) zeolitization occurred

in Pleistcene under two dry seasons. The conversion to zeolite has taken place fairly rapidly, that is within 8000-20000 years. The pH at the time of formation of the zeolites must have been 9.5-10.6. The enrichment of ions was caused by a transportation of capillary water. The dry clima caused an increased salinity which was not favourable to the formation of clays.

The key mechanism of zeolite formation is probably a function of the Si/Al ratio in the gel developed by the saline-alcaline ratio and pH (cf. Mariner and Surdam, 1970). The SiO<sub>2</sub>-gel does not necessarily originate from volcanic glass but can also be a weathering product from feldspars according to the same authors. Then the formation of phillipsite should increase if the Si/Al ratio is low. If the Si/Al ratio is high with increasing pH the formation of clinoptilolite should be favoured. In conglomerates, sandstones, silt- and mudstones zeolites generally coexist with calcite and different iron compounds constitute the cementing mass between the soil elements. Authigene Ca-montmorillonite, Ca-heulandite and polycrystalline quartz occur together in equilibrium in a locality from Upper Cretaceous in Crazy Mountains according to Sims (1969).

In marine deposits it is shown that phillipsite and clinoptilolite are the dominating zeolites in coexistence with montmorillonite but in none-marine deposits analcime together with montmorillonite is more abundant.

Coombs (1952) investigated a Triassic layer altered to a bentonite and with residues of clinoptilolite, volcanic glass, aggregates of heulandite, microcrystalline quartz and clay minerals, analcime and quartz partly transformed to albite (a feldspar).

Later, the same author (1959) made a literature review on a large number of cases where zeolites act as a cementing substance in sandstones, siltstones, arcoses and mudstones. The occurrence of natural zeolites with reference to temperature and depth in some selected localities is illustrated by Table 4, (Coombs, 1959).

Table 4. Temperature of occurrence of some natural zeolites and related minerals.

Mineral	Occurrence	Temperati (T <sup>O</sup> C)	re Depth (m)
Phillipsite Chabazite, phillipsite, natrolite	Deep sea sediments Masonry, Roman baths	0 <sup>O</sup> 40-70 <sup>O</sup>	4000-5000 Surface
Clinoptilolite, analcime	Diagenesis	Low	?
Stilbite	Hunters, Boulder Hot Springs	?64 <b>-</b> ?73 <sup>0</sup>	Surface
Clinoptilolite	Yellowstone	125 <sup>O</sup>	19-26
Analcime	Yellowstone	125 <b>-</b> 155 <sup>0</sup>	26-60
Mordenite	Wairakei	150 <b>-</b> 230 <sup>O</sup>	73-300
Heulandite	Wairakei	within	
Lammonite	Wairakei	195 <b>–</b> 220 <sup>0</sup>	150-275
Warakite	Wairakei	200 <b>-</b> 250 <sup>O</sup>	180-600
Prebnite	Wairakei	~2000	~100
Albite	Wairakei	160-240°	100-600
Adularia	Wairakei	230 <b>-</b> 250 <sup>O</sup>	385-650
Zeolite and adularia	Steam Boat Springs*	170 <sup>O</sup>	52

Note (1) The maximum temperatures recorded for the Wairakei bore holes are 250-260°C.

Coombs stated that zeolites are stable minerals at low temperatures or, under special circumstances, at a small depth. This gives open pores while at greater depth with increasing pressure minor pores are developed under expelling of water. The zeolites will be less stable and an albitization can occur under such circumstances.

<sup>(2)</sup> The appearance of albite and other minerals at abnormally low temperatures and shallow depths in some Wairakei holes suggest that in these cases they may have been deposited under an earlier regime of higher temperatures.

<sup>\*</sup> S White (1955)

Further Coombs (1959) showed that analcime and heulandite can coexist with quartz and closed grain phyllosilicates. He also mentioned that Rengarten (1950) showed that authigenic zeolites occur as cementing substance in many Russian sedimentary rocks from Perm to Tertiary.

Investigations by Sheppard (1973) indicate that neither analcime nor K-feldspar originate directly from the volcanic glass. The formation passes through other zeolite stages both for analcime and K-feldspar. The last mentioned mineral can originate from analcime if the conditions are suitable.

"The paragenesis of silicate minerals in the tuffaceous rocks is attributed to chemical variables of the pore water, such as the Na<sup>+</sup> + K<sup>+</sup> : H<sup>+</sup> ratio, Si : Al ratio, the proportion of cations and the activity of H<sub>2</sub>O."Sheppard and Gude (1972) stated that conglomerates, sandstones and siltstones in the "Big Sandy Formation" are often cemented by calcite, clay minerals, zeolites and opal. It appears that clinoptilolite and analcime are the most frequent cementing zeolites. Fig 1 shows traces of zeolite cementation. In mudstone from the "Big Sandy Formation" authigenic zeolites and K-feldspars are shown. According to the author analcime is the dominating mineral.

In order to give the reader of this report a conception of the detailed appearance of some zeolites a sequence of scanning microscope pictures is shown here. Figs 2 and 3, however, show rock samples of Wyoming-bentonites. They give a general idea of the tight appearance of the montmorillonite particle arrangement in bentonite. In comparison the zeolite configuration is more open and the crystallites well formed.



Fig 1. Sandstone cemented by finely crystalline clinoptilolite. Unpolarized light. (From Sheppard, 1973).

Analcime, often termed analcite, is generally present in sedimentary rocks and together with K-feldspar. The investigation of the "Big Sandy Formation" show evidence of co-existence of montmorillonite-phillip-site-clinoptilolite and montmorillonite-clinoptilolite-quartz. The stability of the system as concerns geochemistry is not clear. However, it is shown that certain analcime crystals disclose a thin film of montmorillonite (see fig 5). It is also shown that authigenic montmorillonite is replaced by analcime. This indicates instability. In "Big Sandy Formation" there is a clear proof of analcime transformation to K-feldspar (fig 4). The mineral transformation in

"Big Sandy Formation" is considered to depend on differences in the chemistry of the pore water.

According to Sheppard (1973), Huntley (1959, 1962), Garrels and Christ (1965), Hess (1966) we have the following statement concerning the process of formation:

"Zeolites and feldspars are favoured over clay minerals by relatively high alkali ion to hydrogen ion activity ratios and by relatively high silica activities. The high alkali ion to hydrogen ion activity ratio necessary for the formation of zeolites in a tuff can be attained in the depositional environment of a saline, alkaline lake or in the postdepositional environment by hydrolysis and solution of silicic vitric material by subsurface water."

Iijima and Hay (1968) and Surdam and Parker (1972):

"Tuffs in the Eocene Green River Formation of Wyoming are altered to montmorillonite where they were deposed in fresh water, to clinoptilolite and mordenite in slightly saline water, to analcime in moderately saline water and to K-felspar in highly saline water."

The formation of K-feldspar governed by the above statement is obvious in many places according to Sheppard. Probable contributing factors are 1) a low activity of  $H_2O$ , 2) a relatively high  $K^+/H^+$  ratio and 3) a high activity of  $SiO_2$ . A high pH produces an increased solubility of  $SiO_2$  which, however, contributes to a stabilization of K-felspar (Surdam & Parker, 1972).




Fig 2. Rock sample of bentonite from Clay Spur, Wyoming (A.P.I. No 26) (Cretaceous). Bohur & Hughes, 1971.




Fig 3. Rock sample of Wyoming bentonite (A.P.I No 26).
Bohur & Hughes, 1973.



Fig 4. Scanning electron micrograph of large analcime crystals in a matrix of micron-size crystals of potassium feldspar fom a saline-lake tuff near Barstow, California. (Sample 25-43-136).




Fig 5. Scanning electron micrograph of a large analcime crystal coated with montmorillonite from a lacustrine tuff near Tejupan, Oaxaca, Mexico.

Various zeolites are shown in the series of pictures given by Figs 6-10. Fig 6 shows etched crystals of clinoptilolite, the etching being caused by porewater dissolution. Figs 7-10 show open-structured masses of different zeolites. It is quite obvious that such materials are much more permeable than montmorillonitic soils. The brittleness of zeolite crystals can be demonstrated in Fig 9, where a fracture in a chabazite crystal is shown.

In this review I have mentioned a few authors and presented their basic ideas about zeolites, which are of interest to us. These ideas are representative also of a large number of other investigators who are not mentioned specifically in this report.

The author's study has yielded definite objections against the use of zeolites in the buffer mass. They are:

- Cementing properties are observed by many investigators.
- 2. The permeability of pure zeolites is much too high to be accepted for buffer mass components.
- 3. Zeolites are unstable at higher temperatures with increasing depth and pressure. They are easily converted to feldspars.
- 4. Zeolites are brittle. In fact there is not a single geological evidence of a non-cemented quartz-bentonite-zeolite mixture above sea level.
- 5. The heat conductivity is poor  $(\lambda \le 0.2 \text{ W/m}, {}^{\circ}\text{C})$
- 6. We have too little knowledge about their

mechanical properties in a mixture with other minerals.

The positive properties of the zeolites are their good ion exchange properties. On the other hand we do not know enough about their long time fixation ability




Fig 6. Scanning electron micrograph of clinoptilolite from Hungry Valley, Nevada. The severely etched crystals are probably due to pore-water dissolution, after formation in a saline-lake environment.



Fig 7. Scanning electron micrograph of phillipsite laths and prisms from a saline-lake tuff near Kirkland, Arizona. Montmorillonite is also abundant in this sample.




Fig 8. Scanning electron micrograph of phillipsite prisms from a marine tuff near Naples, Italy.

Note the "cracking" of many crystals along cleavage surfaces parallel to the axis of elongation. Montmorillonite is also present in this sample.




Fig 9. Scanning electron micrograph of well-formed chabazite crystals from a marine tuff near Kruft, Germany, currently mined as a pozzolan.




Fig 10. Scanning electron micrograph of an isolated chabazite crystal in a saline-lake tuff near Durkee, Oregon. The surrounding matrix is probably montmorillonite.

## References

Bohor B & Hughes R, 1971 Clays and clay minerals. Vol. 19, pp 49-54.

Boles J, 1971

Synthesis of analcime from natural heulandite and clinop-tilolite. Am. Min. Vol. 56.

Boles J, 1972

Composition, optical properties, cell dimensions, and thermal stability of some heulandite group zeolites. American Mineralogist. Vol. 57.

Coombs D et al, 1959

The zeolite facies, with comments on the interpretation of hydrothermal syntheses. Geochimica et Cosmochimica Acta. Vol. 17, pp 53-107.

Coombs D, 1965

Sedimentary analcime rocks and sodium rich gneisses.
Mineral. Mag. 34, p 144-158.

Couture R, 1977

Composition and origin of palygorskite-rich and mont-morillonite-rich zeolite-containing sediment from the Pacific Ocean. Chemical Geology, 19, p 113-130.

Harbaugh J W, 1968

Stratigraphy and the Geologic Time Scale. Brown Foundations of Earth Science Series.

Hay R, 1963

Zeolitic weathering in Olduvai Gorge, Tanganyika. Geological Society of America Bulletin. V 74, p 1281-1286. Hay R, 1966

Zeolites and Zeolitic Reactions in Sedimentary Rocks.

Special G S A papers, No 85.

Hayashi H & Sudo T, 1957 Zeolite-bearing bentonites. Mineralogical Journ. Vol.2, No 3, pp 196-199.

Hemley J, 1959

Some mineralogical equilibria in the system  $K_2^{O-Al_2O_3-SiO_2-H_2O}$ . Amer. Journ. Sci. 257, pp 241-270.

Iijima A & Hay R, 1968

Analcime composition in tuffs on the Green River Formation, Wyoming. Am. Miner. 53, pp 184-200.

Mariner & Surdam, 1970

Alkalinity and formation of zeolites in saline alkaline lakes. Science 170, p 977-980.

Meier W M, 1964

Zeolite structures Molecular Sieves. Conf. of Soc. Chem. Industr. London, p 10-27.

Mumpton F & Ormsby C, 1976 Morphology of zeolites in sedimentary rocks by scanning electron microscopy. Clays and clay minerals. Vol. 24, pp 1-23.

Rengarten N, 1950

Laumontite and analcime from Lower Jurassic deposits in northern Caucasus. Dokl. Akad. Nauk SSSR, 70, p 485-488. Ross S, 1941

Sedimentary analcite. American Mineralogist 26, p 627-629.

Sheppard R & Gude A, 1973 Zeolites and associated authigenic silicate minerals in tuffaceous rocks of the Big Sandy Formation, Mohave County, Arizona. Geological survey professional paper 830.

Sheppard R, 1971

Clinoptilolite of possible economic value in sedimentary deposits of the conterminous United States. Geological survey bull, 1332-B.

Sims J D, 1969

Thermodynamic model for zeolitic diagenesis in the Livingstone Group, Northern Crazy Mountains, Montana in Abstracts for 1968: Geol. Soc. America, Spec. Paper 121, p 636-637.

Surdam R & Parker R, 1972

Authigenic aluminosilicate minerals in the tuffaceous rocks of the Green River Formation, Wyoming. Bull. Geol. Soc. Am. Vol. 83, pp 689-700.

Velde B, 1977

Clays and clay minerals in natural and synthetic systems. Developments in sedimentology 21. Elsevier.

# Förteckning över tekniska rapporter

- 01. Källstyrkor i utbränt bränsle och högaktivt avfall från en PWR beräknade med ORIGEN
  Nils Kjellbert
  AB Atomenergi 77-04-05
- 02. PM angående värmeledningstal hos jordmaterial Sven Knutsson och Roland Pusch Högskolan i Luleå 77-04-15
- 03. Deponering av högaktivt avfall i borrhål med
  buffertsubstans
  A Jocobsson och R Pusch
  Högskolan i Luleå 77-05-27
- 04. Deponering av högaktivt avfall i tunnlar med
  buffertsubstans
  A Jacobsson, R Pusch
  Högskolan i Luleå 77-06-01
- Orienterande temperaturberäkningar för slutförvaring i berg av radioaktivt avfall
  Roland Blomqvist
  AB Atomenergi 77-03-17
- O6. Groundwater movements around a repository,
  Phase 1, State of the art and detailed study plan
  Ulf Lindblom
  Hagconsult AB 77-02-28
- 07. Resteffekt för KBS del l Litteraturgenomgång Del 2 Beräkningar K Ekberg, N Kjellbert, G Olsson AB Atomenergi 77-04-19

- Utlakning av franskt, engelskt och kanadensiskt glas med högaktivt avfall Göran Blomqvist AB Atomenergi 77-05-20
- O9. Diffusion of soluble materials in a fluid filling a porous medium Hans Häggblom AB Atomenergi 77-03-24
- 10. Translation and development of the BNWL-Geosphere Model
  Bertil Grundfelt
  Kemakta Konsult AB 77-02-05
- Utredning rörande titans lämplighet som korrosionshärdig kapsling för kärnbränsleavfall Sture Henriksson AB Atomenergi 77-04-18
- 12. Bedömning av egenskaper och funktion hos
  betong i samband med slutlig förvaring av kärnbränsleavfall i berg
  Sven G. Bergström
  Göran Fagerlund
  Lars Rombén
  Cement och Betonginstitutet 77-06-22
  - 13. Urlakning av använt kärnbränsle (bestrålad uranoxid) vid direktdeponering
    Ragnar Gelin
    AB Atomenergi 77-06-08
  - 14. Influence of cementation on the deformation properties of bentonite/quartz buffer substance R. Pusch Högskolan i Luleå 77-06-20

- 15. Orienterande temperaturberäkningar för slutförvaring i berg av radioaktivt avfall Rapport 2
  Roland Blomquist
  AB Atomenergi 77-05-17
- Översikt av utländska riskanalyser samt planer och projekt rörande slutförvaring Åke Hultgren AB Atomenergi augusti 1977
- 17. The gravity field in Fennoscandia and postglacial crustal movements

  Arne Bjerhammar

  Stockholm augusti 1977
- 18. Rörelser och instabilitet i den svenska berggrunden
  Nils-Axel Mörner
  Stockholms universitet augusti 1977
- 19. Studier av neotektonisk aktivitet i mellersta och norra Sverige, flygbildsgenomgång och geofysisk tolkning av recenta förkastningar Robert Lagerbäck
  Herbert Henkel
  SGU september 1977
- 20. Tektonisk analys av södra Sverige Vättern - Norra Skåne Kennert Röshoff Erik Lagerlund Luleå och Lund september 1977
- 21. Earthquakes of Sweden 1891-1957
  1963-1972
  Ota Kulhänek
  Rutger Wahlström
  Uppsala universitet september

22. The influence of rock movement on the stress/strain situation in tunnels or bore holes with radioactive consisters embedded in a bentonite/quartz buffer mass.

Roland Pusch

Högskolan i Luleå 1977-08-22

23. Water uptake in a bentonite buffer mass.

A model study.

Roland Pusch

Högskolan i Luleå 1977-08-22

24. Beräkning av utlakning av vissa fissionsprodukter och aktinider från en cylinder av franskt glas.

Göran Blomqvist

AB Atomenergi 1977-07-27

25. Blekinge kustgnejs, Geologi och hydrogeologi.

I Larsson KTH
T Lundgren SGI
Ulf Wiklander SGU
Stockholm, augusti 1977

26. Bedömning av risken för fördröjt brott i titan. Kjell Pettersson AB Atomenergi 1977-08-25

27. A short review of the formation, stability and cementing properties of natural zeolites. Arvid Jacobsson Högskolan i Luleå 1977-10-03

28. Värmeledningsförsök på buffertsubstans av bentonit/pitesilt.

Sven Knutsson

Högskolan i Luleå 1977-09-20

- 29. Deformationer i sprickigt berg Ove Stephansson Högskolan i Luleå 1977-09-28
- 30. Retardation of escaping nuclides from a final depository
  Ivars Neretnieks
  Kungliga Tekniska Högskolan Stockholm 1977-09-14
- 31 Bedömning av korrosionsbeständigheten hos material avsedda för kapsling av kärnbränsle-avfall. Lägesrapport 1977-09-27 samt kompletterande yttranden.

  Korrosionsinstitutet och dess referensgrupp